



Standard Specification for High-Strength Low-Alloy Structural Steel Plate With Atmospheric Corrosion Resistance¹

This standard is issued under the fixed designation A871/A871M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers high-strength low-alloy steel plate intended for use in tubular structures and poles or in other suitable applications. Two grades, 60 and 65, may be provided as-rolled, normalized or quenched and tempered as required to meet the specified mechanical requirements.

1.2 The atmospheric corrosion resistance of this steel in most environments is substantially better than that of carbon structural steels with or without copper addition (see **Note 1**). When properly exposed to the atmosphere, this steel can be used bare (unpainted) for many applications.

NOTE 1—For methods of estimating the atmospheric corrosion resistance of low-alloy steels, see Guide **G101**.

1.3 When the steel is to be welded, it is presupposed that welding procedures suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification **A6/A6M** for information on weldability.

1.4 Supplementary requirements in accordance with Specification **A6/A6M** are available, but shall apply only when specified by the purchaser at time of ordering.

1.5 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 *ASTM Standards*:²

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.02** on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved May 1, 2014. Published May 2014. Originally approved in 1987. Last previous edition approved in 2012 as A871/A871M – 12. DOI: 10.1520/A0871_A0871M-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
A370 Test Methods and Definitions for Mechanical Testing of Steel Products
A673/A673M Specification for Sampling Procedure for Impact Testing of Structural Steel
G101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

3. General Requirements for Delivery

3.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification **A6/A6M**, for the ordered material, unless a conflict exists in which case this specification shall prevail.

4. Materials and Manufacture

4.1 The steel shall be made to fine grain practice.

5. Heat Treatment

5.1 Grade 65 in thicknesses of $\frac{3}{16}$ to $\frac{3}{4}$ in. [5 to 20 mm] and Grade 60 in thicknesses of $\frac{3}{16}$ to $1\frac{3}{8}$ in. [5 to 35 mm] are normally furnished in the as-rolled condition. The manufacturer has the option to heat treat this material to meet the mechanical requirements of Section 7. Quenched and tempered material shall be heat treated by heating to not less than 1650°F [900°C], holding a sufficient time to attain uniform heat throughout the material, quenching in a suitable medium, and tempering at not less than 1100°F [595°C]. Heat treating temperatures shall be reported on the test certificates.

5.2 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical requirements. The individual manufacturer shall be contacted to determine the actual maximum thickness for each grade and heat treatment method.

6. Chemical Requirements

6.1 The heat analysis shall conform to the chemical requirements of **Table 1**.

6.2 The steel shall conform on product analysis to the chemical requirements of **Table 1**, subject to the product analysis tolerances in Specification **A6/A6M**.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements (Heat Analysis)

Element	Composition, %		
	Type I	Type II	Type IV
Carbon ^A	0.19 max	0.20 max	0.17 max
Manganese ^A	0.80–1.35	0.75–1.35	0.50–1.20
Phosphorus	0.030 max	0.030 max	0.030 max
Sulfur	0.030 max	0.030 max	0.030 max
Silicon	0.30–0.65	0.15–0.50	0.25–0.50
Nickel	0.40 max	0.50 max	0.40 max
Chromium	0.40–0.70	0.40–0.70	0.40–0.70
Molybdenum	0.10 max
Copper	0.25–0.40	0.20–0.40	0.30–0.50
Vanadium	0.02–0.10	0.01–0.10	...
Columbium	0.005–0.05 ^B

^A For each reduction of 0.01 percentage point below the specified maximum for carbon, an increase of 0.06 percentage point above the specified maximum for manganese is permitted, up to a maximum of 1.50 %.

^B For plates under ½ in. [13 mm] in thickness, the minimum columbium is waived.

6.3 The atmospheric corrosion-resistance index, calculated on the basis of the heat analysis for the steel, as described in Guide **G101**—Predictive Method Based on the Data of Larabee and Coburn, shall be 6.0 or higher.

NOTE 2—The user is cautioned that the Guide **G101** (Predictive Method Based on the Data of Larabee and Coburn) for calculation of an atmospheric corrosion-resistance index has only been verified for the composition limits stated in that guide.

6.4 When required, the manufacturer shall supply evidence of corrosion resistance satisfactory to the purchaser.

7. Mechanical Requirements

7.1 Tension Tests:

7.1.1 The steel as represented by the tension test specimens shall conform to the tensile requirements of **Table 2**.

7.1.2 For adjustments in **Table 2** percentage elongation requirements for material thickness under 0.312 in. [8 mm] and over 3.5 in. [90 mm], see Specification **A6/A6M**.

7.2 Charpy V-Notch Impact Tests:

TABLE 2 Tensile Requirements^A

Grade	Yield Strength ^B min. ksi [MPa]	Tensile Strength min. ksi [MPa]	Minimum Elongation, % ^C	
			In 8 in. [200 mm]	In 2 in. [50 mm]
60	60 [415]	75 [520]	16	18
65	65 [450]	80 [550]	15	17

^A For plates wider than 24 in. [600 mm], the test specimen is taken in the transverse direction. See Tension Tests section of Specification **A6/A6M**.

^B Measured at 0.2 % offset or 0.5 % extension under load as described in Determination of Tensile Properties section of Test Methods **A370**.

^C For plates wider than 24 in. [600 mm], the elongation requirement is reduced three percentage points.

7.2.1 The steel, as represented by the Charpy V-Notch test, shall conform to the impact test requirements of **Table 3**.

7.2.2 If more stringent impact requirements are required, they shall be negotiated between the purchaser and the manufacturer.

8. Test Specimens and Number of Tests

8.1 The purchaser shall indicate on the purchase order the frequency of Charpy V-Notch Impact Testing, as provided for in Specification **A673/A673M**. If the purchase order does not specify the frequency, “H” testing frequency shall be supplied.

9. Keywords

9.1 as-rolled; atmospheric corrosion resistance; high-strength; low-alloy; normalized; plate; poles; quenched; steel; structural steel; tempered; tubular structures

TABLE 3 Charpy V-Notch Impact Test Requirements

Plate Thickness in [mm]	Absorbed Energy ft-lb [J]	Temperature °F [°C]
Up to ½ [12] incl	15 [20]	0 [–18]
Over ½ [12]	15 [20]	– 20 [–29]

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order or contract. Standardized supplementary requirements for use at the option of the purchaser are listed in Specification **A6/A6M**.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A871/A871M – 12) that may impact the use of this standard. (Approved May 1, 2014.)

(1) Modified phosphorous and sulfur limits in **Table 1**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).